

TEST REPORT

BEA250969

Date of report: 2025-12-12

page 1 of 2

Client: Ten Damme B.V.

Address: Bolwerk 9, 7141 JM, Groenlo, THE NETHERLANDS

Order: Fuel testing according ENplus® certification program of wood pellets ENplus® ST.1001:2022

Order date: 2025-12-02

Receipt of samples: 2025-12-02

Sample(s): Wood pellets; "NL 004"

Testing period: 2025-12-02 – 2025-12-12

Sample details: 15 kg pellets in bag class A1 from bagging line; internal sample no.: BEA250969

| parameter ENplus® | limit values A1 | limit values A2 | result class A1 | unit |
|--------------------------------------------|-----------------|-----------------|-----------------|------------------------|
| diameter | 6 ± 1, 8 ± 1 | 6 ± 1, 8 ± 1 | 6,1 | mm (ar) |
| length (3,15 ≤ L ≤ 40 mm) | (3,15 ≤ L ≤ 40) | (3,15 ≤ L ≤ 40) | 17,2 ± 5,0 | mm (ar) |
| length (40 < L ≤ 45 mm) | ≤ 1 | ≤ 1 | 0 | % in mass (ar) |
| length (> 45 mm) | 0 | 0 | 0 | piece(s) |
| share of pellets with a length < 10mm | - | - | 3,2 | % in mass (ar) |
| category L < 20%, 20% ≤ M ≤ 30%, S > 30% | - | - | L | - |
| amount of pellets for length determination | ≥ 100 | ≥ 100 | 1 075 | piece(s) |
| moisture content | ≤ 10,0 | ≤ 10,0 | 6,9 | % in mass (ar) |
| ash content | ≤ 0,70 | ≤ 1,20 | 0,36 | % in mass (db) |
| mechanical durability | ≥ 98,0 | ≥ 97,5 | 99,4 | % in mass (ar) |
| bulk density | 600 ≤ BD ≤ 750 | 600 ≤ BD ≤ 750 | 670 | kg/m ³ (ar) |
| particle density | - | - | 1,31 | g/cm ³ (ar) |
| coarse fines (3,15 ≤ CPF < 5,6 mm) | - | - | 0,1 | % in mass (ar) |
| fines content (< 3,15 mm), bulk | ≤ 1 | ≤ 1 | - | % in mass (ar) |
| fines content (< 3,15 mm), bags | ≤ 0,5 | ≤ 0,5 | 0,1 | % in mass (ar) |
| net calorific value q _{P,net} | ≥ 16,5 | ≥ 16,5 | 17,3 | MJ/kg (ar) |
| net calorific value q _{P,net} | ≥ 4,6 | ≥ 4,6 | 4,8 | kWh/kg (ar) |
| net calorific value q _{P,net} | - | - | 18,7 | MJ/kg (db) |
| net calorific value q _{P,net} | - | - | 5,2 | kWh/kg (db) |
| gross calorific value q _{V,gr} | - | - | 18,7 | MJ/kg (ar) |
| gross calorific value q _{V,gr} | - | - | 5,2 | kWh/kg (ar) |
| nitrogen content | ≤ 0,3 | ≤ 0,5 | 0,08 | % in mass (db) |
| sulphur content | ≤ 0,04 | ≤ 0,04 | 0,006 | % in mass (db) |
| chlorine content | ≤ 0,02 | ≤ 0,02 | <0,005 | % in mass (db) |
| arsenic | ≤ 1 | ≤ 1 | <0,5 | mg/kg (db) |
| cadmium | ≤ 0,5 | ≤ 0,5 | 0,20 | mg/kg (db) |
| chromium | ≤ 10 | ≤ 10 | <1 | mg/kg (db) |
| copper | ≤ 10 | ≤ 10 | <1 | mg/kg (db) |
| lead | ≤ 10 | ≤ 10 | 0,74 | mg/kg (db) |
| mercury | ≤ 0,1 | ≤ 0,1 | <0,075 | mg/kg (db) |
| nickel | ≤ 10 | ≤ 10 | <1 | mg/kg (db) |
| zinc | ≤ 100 | ≤ 100 | 10 | mg/kg (db) |
| shrinking temperature SST | - | - | 1230 | °C |
| deformation temperature DT | ≥ 1200 | ≥ 1100 | 1410 | °C |
| hemisphere temperature HT | - | - | >1500 | °C |
| flow temperature FT | - | - | >1500 | °C |

db... dry basis, ar... as received

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.

| | | |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|   | director in charge  |  |
| | Dr. Viktoria Horvath | |

TEST REPORT

BEA250969

Date of report: 2025-12-12

page 2 of 2

Client: Ten Damme B.V.

Address: Bolwerk 9, 7141 JM, Groenlo, THE NETHERLANDS

Order: Fuel testing according ENplus® certification program of wood pellets ENplus® ST.1001:2022

Order date: 2025-12-02

Receipt of samples: 2025-12-02

Sample(s): Wood pellets; "NL 004"

Testing period: 2025-12-02 – 2025-12-12

Sample details: 15 kg pellets in bag class A1 from bagging line; internal sample no.: BEA250969

testing methods


standard

| | |
|--------------------------------------------|----------------------------------------------------------------|
| diameter and length | ISO 17829:2015 |
| moisture content | ISO 18134-2:2017 |
| ash content | ISO 18122:2022 |
| mechanical durability | ISO 17831-1:2015 |
| finest content < 3,15 mm | ISO 5370:2023 |
| net calorific value /gross calorific value | ISO 18125:2017 |
| bulk density | ISO 17828:2015 |
| carbon, hydrogen, nitrogen content | ISO 16948:2015 |
| chlorine, sulphur content | ISO 16994:2016, quantification according to ISO 10304-1:2016 |
| minor elements | ISO 16968:2015, quantification according to ISO 17294-2:2023 |
| ash melting behaviour | ISO 21404:2020, ash preparation at 815°C, oxidizing atmosphere |
| coarse pellets fines 3,15 < CPF < 5,6 mm | ISO 5370:2023 |
| particle density | ISO 18847:2017 |

remarks

none

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.

| | | |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|   | director in charge  Dr. Viktoria Horvath |  |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|



BEA Institut für Bioenergie GMBH - Accr. certification body acc. to EN ISO/IEC 17065 | Accr. testing laboratory acc. to EN ISO/IEC 17025

1150 Vienna | Avedikstrasse 21 | AUSTRIA | P: +43 1 89093 91 | F: +43 1 89093 92 | www.bioenergy.institute | Email: office@bioenergy.co.at
Legal form: GmbH | Headquarter: Vienna | Comm.reg.No.: FN 331066m | Jurisdiction: Vienna | UID/VAT: ATU 65124117
IBAN: AT47 1200 0529 4901 1803 | SWIFT: BKAUATWW | Bank: Bank Austria AG | EORI: ATEOS1000004531 | CEO: DI Dr. Martin Englisch